

PA 2201
EOS GmbH - Electro Optical Systems
Product Texts
Product Texts

PA 2201, a whitish, a bit more translucent polyamide 12 powder, is in compliance with FDA, 21 CFR, §177.1500 9(b) except for alcoholic foodstuff. Apart from that PA 2201 and PA 2200 have identical material properties. Laser-sintered parts made from PA 2201 possess excellent material properties:

- high strength and stiffness
- good chemical resistance
- excellent long-term constant behaviour
- high selectivity and detail resolution
- various finishing possibilities (e.g. metallisation, stove enamelling, vibratory grinding, tub colouring, bonding, powder coating, flocking)

Typical applications of the material are fully functional plastic parts of highest quality. Due to the excellent mechanical properties the material is often used to substitute typical injection moulding plastics. The biocompatibility allows its use e.g. for prostheses, the high abrasion resistance allows e.g. the realisation of movable part connections.

Mechanical properties	Value	Unit	Test Standard
Izod notched impact strength (+23°C)	4.4	kJ/m ²	ISO 180/1A
Izod impact strength (+23°C)	33	kJ/m ²	ISO 180/1U
Shore D hardness	75	-	ISO 7619-1
Ball indentation hardness	78	MPa	ISO 2039-1

3D Data	Value	Unit	Test Standard
The properties of parts manufactured using additive manufacturing technology (e.g. laser sintering, stereolithography, Fused Deposition Modelling, 3D printing) are, due to their layer-by-layer production, to some extent direction dependent. This has to be considered when designing the part and defining the build orientation.			
Tensile Modulus			ISO 527
X Direction	1700	MPa	
Y Direction	1700	MPa	
Tensile Strength			ISO 527
X Direction	48	MPa	
Y Direction	48	MPa	
Strain at break (X Direction)	15	%	ISO 527
Charpy impact strength (+23°C, X Direction)	53	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C, X Direction)	4.8	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C, X Direction)	1500	MPa	ISO 178
Flexural Strength (X Direction)	58	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
Melting temperature (20°C/min)	176	°C	ISO 11357-1/-3
Vicat softening temperature			ISO 306
50°C/h 10N	181	°C	
50°C/h 50N	163	°C	

Other properties	Value	Unit	Test Standard
Density (lasersintered)	930	kg/m ³	EOS Method
Powder colour (ac. to safety data sheet)	White	-	-

Characteristics
Processing

Laser Sintering, Rapid Prototyping

Chemical Resistance

General Chemical Resistance

Delivery form

Powder

Certifications

Food approval FDA 21 CFR